



Buffalo Felt
Products Corp.

Buffalo Felt Products Corporation
14 Ransier Drive, West Seneca, NY 14224
Phone: (716) 674-7990 Fax: (716) 674-3631
www.buffalofelt.com
Email: salesdesk@buffalofelt.com

F-55 SPECIFICATIONS

Commercial Standard Grade	12R3X
SAE Number	F-55
NTA Number	26R3
GENERAL PROPERTIES	
Minimum Wool Content	75%
Density (1")	12.00 lbs/sq yd
Standard Thickness Range	1/16" to 3/32"
Standard Width	60" to 72"
Color	Gray / Black
PHYSICAL PROPERTIES	
Specific Gravity	0.26
Thermal Condition (70F)	0.30 btu / hr /sq ft / °F / in
Thermal Expansion	0
Air Perm (1/16")	20-50 cfm / sq ft / 0.5" H2O
Liquid Absorption by weight by volume	> 225% (1.0 sp gr) 81%
Capillarity (wicking height, 575 SSU, 70F)	3
Coefficient of Friction	0.37
Vibration Absorption Static load bearing cap/unit area	--
Dynamic Stress Endurance	--
Noise Reduction Coef (1")	0.58
MECHANICAL PROPERTIES	
Tensile Strength (min)	200 psi
Elongation 100% (100 psi)	25
Mullen Bursting Strength (1/8")	200 psi
Split Resistance (min)	--
Hardness Range Shore A	--
Compressibility (10% defl.)	--
Recovery (within 1 min after 10% defl.)	99%
Abrasion Resistance	Good
CHEMICAL AND ENVIRONMENTAL PROPERTIES	
Effect of Sunlight and Oxidation	None
Solvent Resistance and Stability in Oil	Excellent
Acid Resistance, dilute	Good
Concentrated	Fair
Alkali Resistance, dilute	Fair
Concentrated	Low
Temperature Range	-80°F to +200°F
TYPICAL USES	
Anti-squeak strips, anti-drumming and insulation lining laminated to other materials.	



These data were obtained by ASTM D-461 Test Methods, ASTM D-2475 Standards, and NTA Wool Felt Specifications.