



**Buffalo Felt**  
Products Corp.

Buffalo Felt Products Corporation  
14 Ransier Drive, West Seneca, NY 14224  
Phone: (716) 674-7990 Fax: (716) 674-3631  
www.buffalofelt.com  
Email: salesdesk@buffalofelt.com

## F-26 DENSITY AND THICKNESS

Commercial Standard Grade	8R5
SAE Number	F-26
Trade Designation	Soft Pad
Minimum Wool Content	45%
Density Specific Gravity	0.17
Carbon Tetrachloride Soluble (max)	5.0%
Water Soluble (max)	6.0%
Carbon Tetrachloride & Water Soluble (max)	14.0%
Ash (max)	5.0%
Tensile Strength (min)	--
Split Resistance (min)	--
Color	Gray
Standard Width	72"

THICKNESS		WEIGHT	
Nominal (Inches)	Limits (Inches)	Nominal (Lb/sq yd)	Limits (Lb/sq yd)
1/8	0.085 - 0.165	0.90 lb/yd <sup>2</sup>	0.81 - 0.99 lb/yd <sup>2</sup>
1/4	0.194 - 0.306	1.80 lb/yd <sup>2</sup>	1.62 - 1.98 lb/yd <sup>2</sup>
3/8	0.303 - 0.447	2.70 lb/yd <sup>2</sup>	2.43 - 2.97 lb/yd <sup>2</sup>
1/2	0.412 - 0.588	3.60 lb/yd <sup>2</sup>	3.24 - 3.96 lb/yd <sup>2</sup>
3/4	0.630 - 0.870	5.40 lb/yd <sup>2</sup>	4.86 - 5.94 lb/yd <sup>2</sup>
1	0.848 - 1.152	7.20 lb/yd <sup>2</sup>	6.84 - 7.92 lb/yd <sup>2</sup>

