



F-11 SPECIFICATIONS

Commercial Standard Grade	9R2
SAE Number	F-11
NTA Number	18R2
GENERAL PROPERTIES	
Minimum Wool Content	87%
Density (1")	8.48 lbs/sq yd
Standard Thickness Range	1/8" to 1"
Standard Width	72"
Color	Gray
PHYSICAL PROPERTIES	
Specific Gravity	0.18
Thermal Condition (70F)	0.24 btu / hr /sq ft / °F / in
Thermal Expansion	0
Air Perm (1/16")	75-150 cfm / sq ft / 0.5" H2O
Liquid Absorption by weight by volume	> 375% (1.0 sp gr) 88%
Capillarity (wicking height, 575 SSU, 70F)	2.5
Coefficient of Friction	0.37
Vibration Absorption Static load bearing cap/unit area	Low
Dynamic Stress Endurance	High - Medium
Noise Reduction Coef (1")	0.64
MECHANICAL PROPERTIES	
Tensile Strength (min)	200 psi
Elongation 100% (100 psi)	35
Mullen Bursting Strength (1/8")	60 psi
Split Resistance (min)	6 lb/2" width
Hardness Range Shore A	15-25
Compressibility (10% defl.)	4 psi
Recovery (within 1 min after 10% defl.)	99%
Abrasion Resistance	Fair
CHEMICAL AND ENVIRONMENTAL PROPERTIES	
Effect of Sunlight and Oxidation	None
Solvent Resistance and Stability in Oil	Excellent
Acid Resistance, dilute	Excellent
Concentrated	Fair - Good
Alkali Resistance, dilute	Fair
Concentrated	Low
Temperature Range	-80°F to +200°F
TYPICAL USES	
Dryer drum seals, impregnated packing, insoles, insulation; oil, dust and mud shields.	

